

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 February 2005 (10.02.2005)

PCT

(10) International Publication Number
WO 2005/013362 A1

(51) International Patent Classification⁷: **H01L 23/373**,
23/427

(74) Agents: **VINCENT, Lester, J.** et al.; Blakely, Sokoloff,
Taylor & Zafman, 12400 Wilshire Boulevard, 7th Floor,
Los Angeles, CA 90025 (US).

(21) International Application Number:
PCT/US2004/024269

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(22) International Filing Date: 28 July 2004 (28.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/631,912 30 July 2003 (30.07.2003) US

(71) Applicant (*for all designated States except US*): **INTEL
CORPORATION** [US/US]; 2200 Mission College Boul-
vard, Santa Clara, CA 95052 (US).


(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **MATAYABAS,
James** [US/US]; 1380 West Saragosa Place, Chandler, AZ
85224 (US). **KONING, Paul** [US/US]; 722 West Raven
Drive, Chandler, AZ 85248 (US).

[Continued on next page]

(54) Title: PHASE CHANGE THERMAL INTERFACE MATERIALS USING POLYESTER RESIN AND CLAY FILLED



(57) Abstract: An embodiment of a phase change TIM of this invention comprises a polyester matrix with melting temperature near or below operating temperature (typically less than about 130°C), thermally conductive filler with bulk thermal conductivity greater than about 50 W/mK, and optionally other additives. The polyester resin has improved thermo-oxidative stability compared to the polyolefin resins, thereby providing improved reliability performance during test.

WO 2005/013362 A1



Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

PHASE CHANGE THERMAL INTERFACE MATERIALS USING POLYESTER RESIN AND CLAY FILLER

BACKGROUND OF THE INVENTION

1). Field of the Invention

[0001] This invention relates to phase change thermal interface materials (TIM's) comprising polyester resins and electronic devices with such TIM's.

2). Discussion of Related Art

[0002] Today's semiconductor devices, whether discrete power or logic integrated circuits, are smaller, run faster, do more and generate more heat. Due to increased power, some desktop microprocessors dissipate heat in the range of 50 to 100 watts. These power levels require thermal management techniques involving large-capacity heat sinks, good air flow, and careful management of thermal interface resistances. A well-designed thermal management program will keep operating temperatures within acceptable limits in order to optimize device performance and reliability.

[0003] Semiconductor devices are kept within their operating temperature limits by transferring junction-generated waste heat to the ambient environment, such as the surrounding room air. This is best accomplished by attaching a heat sink to the semiconductor package surface, thus increasing the heat transfer between the hot case and the cooling air. A heat sink is selected to provide optimum thermal performance. Once the correct heat sink has been selected, it must be carefully joined to the semiconductor package to ensure efficient heat transfer through this

newly formed thermal interface.

[0004] Thermal materials have been used to join a semiconductor package and a heat sink, and to dissipate the heat from the semiconductor devices, such as microprocessors. A TIM typically comprises a polymer matrix and a thermally
5 conductive filler. The TIM technologies used for electronic packages encompass several classes of materials such as epoxies, greases, gels, and phase change materials.

[0005] Metal filled epoxies commonly are highly conductive materials that thermally cure into highly crosslinked materials. However, metal filled epoxies
10 exhibit localized phase separation due to package thermo-mechanical behavior and their high modulus leads to delamination at the interfaces.

[0006] Thermal greases display good wetting and ability to conform to the interfaces, no post-dispense processing, and high-bulk thermal conductivity. However, greases tend to migrate out from between the interfaces under cyclical
15 stresses encountered during temperature cycling, a phenomenon known as "pump out."

[0007] Gels typically comprise a crosslinkable silicone polymer, such as vinyl-terminated silicone polymer, a crosslinker, and a thermally conductive filler. After cure, gels are crosslinked filled polymers, and the crosslinking reaction
20 provides cohesive strength to circumvent pump-out issues exhibited by greases during temperature cycling. Their modulus (E') is low enough so that the material can still dissipate internal stresses and prevent interfacial delamination, but not low enough to survive the reliability-stressing test.

[0008] Phase change materials (PCMs) are in a class of materials that undergo a transition from a solid to a liquid phase with the application of heat. These materials are in a solid state at room temperature and are in a liquid state at die operating temperatures. When in the liquid state, PCMs readily conform to surfaces and provide low thermal interfacial resistance. PCMs offer ease of handling and processing due to their availability in a film form and the lack of post-dispense processing. However, from a formulation point, the polymer and filler combinations that have been utilized in PCMs restrict the bulk thermal conductivities of these materials. In general pump-out, bleed-out, and dry-out are continuing reliability issues for phase change TIMs. Commercial phase change thermal interface materials (such as Chomerics T454) are polyolefin-based. Because of their hydrocarbon chemical structure, polyolefins rapidly degrade in oxygen above about 125°C, with a corresponding increase in thermal resistance (Rja); see Figure 1. This presents a high risk for thermo-oxidative degradation over time at operating temperatures below about 110°C and is a show-stopper for applications with operating temperatures above 110°C.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] The invention is described by way of examples with reference to the accompanying drawings, wherein:

[0010] Figure 1 is a graph of Rja vs. time of bake at 125°C for a test vehicle comprising a conventional Chomerics T454 phase change material;

[0011] Figure 2 is a graph of thermographic material (TGA) in air showing improved

thermo-oxidative stability for the polyester resins in Examples 1 and 2 compared to the polyolefin-based commercial material T454 from Chomerics;

[0012] Figure 3 is a cross-sectional view of a semiconductor package that uses an embodiment of a thermal interface material of the invention;

5 [0013] Figure 4 is a schematic representation of layered clay material useful in an embodiment of a thermal interface material of the invention; and

[0014] Figure 5 is a schematic view of the platelets of clay and the tortuous path created by the platelets of clay that result in barrier improvement in the nanocomposite, according to an embodiment of this invention.

10

DETAILED DESCRIPTION OF THE INVENTION

[0015] This invention provides a base resin that has form and function similar to that of current polyolefins, yet provides significantly improved thermo-oxidative stability, which provides a thermal solution for applications with high junction
15 temperatures (T_j 's) and provides improved bake stability for applications with lower T_j 's.

General Formulation

[0016] An embodiment of a phase change TIM of this invention comprises a polyester matrix with melting point near or below the operating temperature
20 (typically less than about 130°C), thermally conductive filler with bulk thermal conductivity greater than about 50 W/mK, and optionally other additives.

[0017] The polyester resin has improved thermo-oxidative stability compared to

the polyolefin resins, thereby providing improved reliability performance, especially during bake and HAST testing.

[0018] The phase change TIM's can be used in a wide variety of applications.

They are especially useful as thermal interface material between an electronic

5 package and a heat sink or heat plate. They can be used for a variety of electronic

packages, including organic flip-chip, ceramic flip-chip, and wirebonded

packages. Optionally, the package may comprise a heat sink and another thermal

interface material between the die and the heat sink. The TIM's may be used as

the first-level TIM (between the die and a heat spreader), as the second-level TIM

10 (between the heat spreader and heat sink), and as the TIM for a bare die (between

the die and heat plate or heat sink). The electronic devices of this invention have

improved reliability performance.

[0019] The phase change thermal interface materials (PCM's) comprise one or

more polyester matrix polymers, one or more thermally conductive fillers, and

15 optionally other additives. The PCM's are useful as thermal interface materials

for removing heat from semiconductor components, and they have improved

reliability performance resulting from improved thermo-oxidative stability of the

polyester resin.

[0020] It is preferred that polyester resin have a melting point slightly above

20 room temperature (i.e., about 40°C), yet below the operating temperature of the

electronic device (typically less than about 130°C). If desired, the polyester resin

may comprise reactive groups for crosslinking. Polycaprolactone is a preferred

polyester resin. If desired, other resins may be included to modify/control

desired properties, such as modulus, viscosity, and moisture adsorption.

Examples of resin additives include polyolefins, polystyrenes, polyacrylates, polyamides, polyimides, polyarylates, epoxies, and the like, or their mixtures.

[0021] The thermally conductive filler should preferably have bulk thermal

5 conductivity greater than about 50 W/mK. Examples of useful fillers include ceramics, such as zinc oxide, aluminum oxide, boron nitride, aluminum nitride, and the like; metals, such as aluminum, copper, silver, and the like; solders, such as indium, tin, and the like; and their combinations. Typically, the amount of thermally conductive filler is about 10 to 90 percent by weight (wt%), depending
10 on such factors as the desired bulk thermal conductivity and the selection of the fillers.

[0022] Examples of useful additives include surfactants, coupling agents, adhesion modifiers, wetting agents, colorants, stabilizers, and the like.

Organoclay materials may be included to further improve thermo-oxidative
15 stability and decrease diffusion of gases and small molecules for still further reliability improvement.

[0023] The PCM's may be mixed by a wide variety of processes, including batch, semi-continuous, and continuous processes, optionally with use of a solvent or a dilutant. In one embodiment of this invention, the PCM is prepared as thin film
20 with a backing layer and a release layer as a drop-in replacement for the current form and function of PCM's known in the art today.

Examples

[0024] **Example 1:** This example is representative of a polyester-based phase change thermal interface material that has significantly improved thermo-oxidative stability: 50 grams of toluene, 50 grams of polycaprolactone (POLYOL 1278® from Dow Chemical Company, Inc.) with a melting point of 50°C, and 50 grams of BN are mixed at 80°C in a Ross double planetary mixer for 3 hrs. The material is cast onto 3-mil thick Mylar® film and dried at 100°C to a final thickness of about 13 mils. The material is evaluated by an interfacial tester at 90 psi and 90°C and found to have a thermal resistance of 0.1°C cm²/W. As illustrated in Figure 2, TGA analysis in air shows that the material begins to degrade above about 200°C, with significant degradation occurring after about 300°C.

[0025] **Example 2:** This example is representative of a polyester organoclay nanocomposite-based phase change thermal interface material that has significantly improved thermo-oxidative stability: 50 grams of toluene, 49 grams of polycaprolactone (POLYOL 1278® from Dow Chemical Company, Inc.) with a melting point of 50°C, 49 grams of BN, and 2 grams of organoclay (Nanomer® I.30P from Nanocor, Inc.) are mixed at 80°C in a Ross double-planetary mixer for 3 hours. The material is cast onto 3-mil-thick Mylar® film and dried at 100°C to a final thickness of about 13 mils. The material is evaluated by an interfacial tester at 90 psi and 90°C and found to have a thermal resistance of 0.1°C cm²/W. As illustrated in Figure 2, TGA analysis in air shows that the material begins to degrade above about 200°C, with significant degradation occurring after about 320°C.

[0026] **Comparative Example:** This example is representative of a polyolefin-based phase change thermal interface material: 50 grams of toluene, 50 grams of alpha-olefin resin (ADMER® AT1030A from Mitsui Chemicals America, Inc.) with a softening point of 59°C, and 50 grams of BN are mixed at 80°C in a Ross double-planetary mixer for 3 hours. The material is cast onto 3-mil-thick Mylar® film and dried at 100°C to a final thickness of about 13 mils. The material is evaluated by an interfacial tester at 90 psi and 90°C and found to have a thermal resistance of 0.1°C cm²/W. As illustrated in Figure 2, TGA analysis in air shows that the material begins to degrade above about 100°C, with significant degradation occurring after about 200°C.

Semiconductor Package

[0027] The following figures refer to apparatus and methods for a heat transfer apparatus adapted to be used on a semiconductor or an electronic device such as, but not limited to, a microprocessor for use in a computer. The scope of the invention is not to be limited to microprocessors specifically, nor computer assemblies in general. The scope of the invention includes, but is not limited to, any device or apparatus requiring the benefits of a heat transfer apparatus that includes a thermal interface material of this invention.

[0028] Figure 3 illustrates a cross-sectional view of a semiconductor package 100 which uses an embodiment of the invention. The semiconductor package 100 includes a substrate 101, having a semiconductor device 103 mounted on a top surface of the substrate 101. The semiconductor device 103 is a microelectronic

die having an integrated circuit formed therein. In one embodiment, the substrate 101 is a printed circuit board. In another embodiment, the substrate 101 may be a different material, such as silicon or ceramic.

[0029] The semiconductor device 103 is mechanically and electrically coupled to the top surface of the substrate 101 via a plurality of solder bump connections 102. In some embodiments, the gap may be filled with an epoxy underfill material (not shown). The substrate 101 contains at least one wiring layer (not shown) that electrically connects the device to pins or balls located along the bottom surface of the substrate 101. The solder balls 102 are placed in an array and are commonly referred to as a ball grid array. Because the semiconductor device 103 is flipped into place so the solder balls 102 electrically and mechanically connect to pads or lands in the substrate 101, the semiconductor device 103 is sometimes referred to as a flip-chip.

[0030] A first thermal plate in the form of a heat spreader 105 is thermally coupled to the major surface of the semiconductor device 103 that does not carry solder balls 102 through a compliant heat-transfer medium 104 known as a thermal interface material. In one embodiment, the thermal interface material is a nanocomposite phase change thermal interface material that includes one or more matrix polymers, one or more thermally conductive fillers, and one or more clay materials. The nanocomposite phase change material 104 fills small voids in the major surface of the back side of the semiconductor device 103 (the major surface without solder balls) and the corresponding surface of the heat spreader 105 to which the semiconductor device 103 is attached. The back side of the

semiconductor device 103 and the surface of the heat spreader 105 to which the semiconductor device 103 is attached is a thermal interface.

[0031] The heat spreader 105 is further attached to the substrate using a sealant material 107. The sealant material 107 surrounds the device 103 and fills the gap between the substrate 101 and the heat spreader 105, forming a completely enclosed cavity containing the device 103. The use of the sealant material 107 allows for a more flexible bond between the substrate 101 and the heat spreader 105. In one embodiment, the sealant material may be silicone or another sealant material. The flexible bond can help to compensate for differing coefficients of thermal expansion (CTE) between the heat spreader 105 and the substrate 101, resulting in a more consistent heat conduction pathway. In other embodiments, the sealant material is replaced with a contiguous wall of metal. The use of the sealant material 107 shown results in a lighter semiconductor package 100 than one where the sealant material is replaced with a wall of metal.

[0032] A heat sink 106 is attached to the heat spreader 105 at another thermal interface using a thermal interface material 108. The heat spreader 106 includes a second thermal plate 110 and a plurality of fins 112 extending from the second thermal plate 110. In one embodiment, the thermal interface material 108 is the same material as the thermal interface material 104. In another embodiment, the thermal interface material 108 is a different nanocomposite phase change thermal interface material that includes one or more matrix polymers, one or more thermally conductive fillers, and one or more clay materials. The heat sink 106 allows for the more rapid dissipation of heat due to increased surface area for

cooling. It should be noted that in some embodiments, one of the thermal interface material 104 and the thermal interface material 108 may not be a nanocomposite phase change thermal interface material that includes one or more matrix polymers, one or more thermally conductive fillers, and one or more clay materials. One of the thermal interface materials can be another type of thermal interface material. Thermal interface materials typically include a polymer matrix and a thermally conductive filler, and encompass several classes of materials such as epoxies, greases, gels, and phase change materials. It should also be noted that Figure 3 is one example of a package 100 that uses a thermal interface material 104, 108 and that there are other types of packages. Furthermore, it should be noted that the thickness of the thermal interface material 104 and the thickness of the thermal interface material 108, as shown in Figure 1, are thick for the purpose of illustrating the position of the thermal interface materials 104 and 108. The resistance to heat transfer across a thermal interface, as shown by the following equations and text, is directly proportional to the thickness of the interface. Therefore, for the sake of thermal efficiency, it is desirable to make the thermal interface as thin as possible.

[0033] Another common style of semiconductor package is similar to that shown in Figure 1. In this style of package (sometime known as bare die), the heat spreader 104 and thermal interface material 108 are omitted and a thermal plate portion of the heat sink is in direct contact with the TIM material 104.

[0034] The rate of conductive heat transfer, Q , across the interface is given by:

$$Q = \frac{kA (T_c - T_s)}{L}$$

5 where k is the thermal conductivity of the interface, A is the heat transfer area, L is the interface thickness and T_c and T_s are the device case and heat sink temperatures. The thermal resistance of a joint, R_{c-s}, is given by

$$R_{c-s} = \frac{(T_c - T_s)}{Q}$$

10

and on rearrangement,

$$R_{c-s} = \frac{L}{kA}$$

15

[0035] Thus, the thermal resistance of the joint is directly proportional to the joint thickness and inversely proportional to the thermal conductivity of the medium making up the joint and to the size of the heat transfer area. Thermal resistance is minimized by making the joint as thin as possible, increasing joint thermal conductivity by eliminating interstitial air, and making certain that both surfaces are in intimate contact.

20

[0036] Attaching a heat sink to a semiconductor package requires that two solid surfaces be brought together into intimate contact. Unfortunately, no matter how well-prepared, solid surfaces are never really flat or smooth enough to permit intimate contact. All surfaces have a certain roughness due to microscopic hills and valleys. Superimposed on this surface roughness is a macroscopic non-

25

planarity in the form of a concave, convex, or twisted shape. As two such surfaces are brought together, only the hills of the surfaces come into physical contact. The thermal interface material must be thin and must also fill the valleys that are separated and form air-filled gaps.

5 Addition of Clay

[0037] The nanocomposite phase change materials used as thermal interface materials may include one or more clay materials. By exfoliating the clay into the thermal interface material, the clay particles become dispersed as very small platelets with a high aspect ratio (typically greater than 200) and a high surface
10 area. Because of the high aspect ratio and surface area, very minor amounts of clay, typically less than 10 wt%, are required, and as little as 0.5 wt% provides significant, desired improvements in the thermal interface material. The clay particles improve the reliability and performance of TIM materials by slowing diffusion of oxygen and water through the thermal interface material. The
15 resulting nanocomposite phase change material has improved high-acceleration stress test ("HAST") performance, and slows the release of volatile components for reduced pump-out, bleed-out, and dry-out of the thermal interface material. The clay particles also improve the thermo-oxidative stability of the TIM for improved bake and thermal cycling ("TC") performance.

20 [0038] The PCM's of the present invention may comprise less than about 25 weight percent, preferably less than about 5 weight percent of clay materials that comprise platelet particles. Generally, the clay materials useful in this invention are an

agglomeration of individual platelet particles that are closely stacked together like cards, in domains called tactoids. The individual platelet particles of the clays preferably have a thickness of less than about 2 nm and a diameter greater than about 10 nm, typically about 10 to about 3000 nm. Useful clay materials include natural, synthetic, and modified phyllosilicates. Natural clays include smectite
5 clays, such as montmorillonite, saponite, hectorite, mica, vermiculite, bentonite, nontronite, beidellite, volkonskoite, magadite, kenyaite, and the like. Synthetic clays include synthetic mica, synthetic saponite, synthetic hectorite, and the like.

Modified clays include fluoronated montmorillonite, fluoronated mica, and the like.

10 Moreover, the layered clay materials are typically swellable free-flowing powders having a cation exchange capacity from about 0.3 to about 3.0 milliequivalents per gram of mineral (meq/g), preferably from about 0.90 to about 1.5 meq/g.

[0039] In an embodiment of this invention, an intercalated layered clay material

is prepared by the reaction of a swellable layered clay with one or more organic
15 cations, preferably ammonium compounds, to effect partial or complete cation exchange. Numerous methods to modify layered clays with organic cations are known, and any of these may be used in the practice of this invention. One

embodiment of this invention is the organic modification of a layered clay with an organic cation salt by the process of dispersing a layered clay or mixture of clays
20 into hot water (50 to 80°C), adding the organic cation salt (neat or dissolved in water or alcohol) with agitation, then blending for a period of time sufficient for the organic cations to exchange most of the metal cations present in the galleries between the layers of the clay material(s). Then, the organically modified layered

clay material(s) is isolated by methods known in the art, including filtration, centrifugation, spray drying, and their combinations. Typically, the organoclay is reduced in particle size to less than about 100 microns by methods known in the art, including milling, grinding, pulverizing, hammer milling, jet milling, and
5 their combinations.

[0040] The clay may be further treated for the purposes of aiding exfoliation in the composite and/or improving the strength of the polymer/clay interface. Any treatment that achieves the above goals may be used. Examples of useful treatments include intercalation with water-soluble or water-insoluble polymers, organic reagents or monomers, silane compounds, metals or organometallics,
10 and/or their combinations.

[0041] Preferably, the clays are dispersed in the formulation so that most of the clay material exists as individual platelet particles, small tactoids, and small aggregates of tactoids with dimensions of less than about 20 nm. Compositions with the higher concentration of individual platelet particles and fewer tactoids or
15 aggregates are preferred. Without being bound by any particular theory, it is believed that the improved properties of the materials of this invention are derived by the unique property of the platelet particles to reduce diffusion of gasses and low molecular weight components through the material.

[0042] Figure 4 is a schematic representation of layered clay material 210 useful in an embodiment of a thermal interface material of the invention. The clay forms layers having aspect ratios of approximately 200. As shown in Figure 4, the thickness of a layer 220 of clay is approximately 1 nm. The length of the layer 220
20

of clay is approximately 200 nm. Figure 4 also shows the structure of a clay used in one embodiment of the invention. The layers of clay, such as layer 220, reduce the rate of diffusion of gases and low molecular weight components through the nanocomposite phase change material forming the thermal interface material.

5 The gases and low molecular weight components are depicted as small round objects, such as 230, 232, and 234 in Figure 2.

[0043] Figure 5 is a schematic view of the platelets of clay which form layers of clay, and the tortuous path created by the platelets of clay that result in barrier improvement in the nanocomposite, according to an embodiment of this

10 invention. One theory for explaining the improvements is the tortuous path theory, in which the permeant, such as the gases and low molecular weight components depicted by reference numbers 230, 232, and 234 in Figure 4, is said to have to permeate a longer distance due to the presence of the platelet particles with a large aspect ratio. Figure 5 shows three layers or platelets of clay 310, 312, and 314. The length of the path through the material without the platelets is depicted by P_{Matrix} . The length of the path through the material with the platelets 310, 312, and 314 is depicted by $P_{Nanocomposite}$. In short, the platelets 310, 312, and 314 create a tortuous path that lengthens the path length of $P_{Nanocomposite}$ when compared to P_{Matrix} .

20 [0044] There is also an equation for the tortuous path mechanism for barrier improvement, which is as follows:

$$P_{Nanocomposite} = \frac{(\text{Matrix Volume Fraction}) * (P_{matrix})}{1 + (\text{platelet Volume Fraction}) * (\text{Platelet Aspect Ratio}) / 2}$$

where,

P_{Matrix} is the permeability of the matrix material alone

$P_{\text{Nanocomposite}}$ is the permeability of the nanocomposite formulation

5

Matrix Volume Fraction is the volume fraction of matrix (e.g., polymer and organic additives)

Platelet Volume Fraction is the volume fraction of clay Material

10

Platelet Aspect Ratio is a measure of the average diameter to length of the platelet

[0045] While certain exemplary embodiments have been described and shown in the accompanying drawings, it is to be understood that such embodiments are merely illustrative and not restrictive of the current invention, and that this invention is not restricted to the specific constructions and arrangements shown and described since modifications may occur to those ordinarily skilled in the art.

CLAIMS

What is claimed:

1. An electronic package, comprising:
 - 5 a first device including a microelectronic die having an integrated circuit;
 - a second device including a first thermal plate; and
 - a thermal interface material between and in contact with surfaces of the first and second devices, the thermal interface material including:
 - at least one polyester matrix material; and
 - 10 at least one thermally conductive filler dispersed within the polyester matrix material.
2. The electronic package of claim 1, wherein the thermal interface material is a phase change material.
- 15 3. The electronic package of claim 1, wherein the polyester matrix material has a melting point between 40°C and 130°C.
4. The electronic package of claim 1, wherein the polyester matrix material has improved thermo-oxidative stability compared to a polyolefin resin.
- 20 5. The electronic package of claim 1, wherein the polyester matrix material is polycaprolactone.

6. The electronic package of claim 1, wherein the thermal interface material further includes an additive to modify at least one of modulus, viscosity, and moisture adsorption.

5

7. The electronic package of claim 6, wherein the additive is a resin.

8. The electronic package of claim 6, wherein the additive is at least one of polyolefin, polystyrene, polyacrylate, polyamide, polyimide, polyarylate, and epoxy.

10

9. The electronic package of claim 1, wherein the thermally conductive filler has a bulk thermal conductivity greater than 50 W/mK.

15 10. The electronic package of claim 1, wherein the thermally conductive filler includes at least one of a ceramic, a metal, and a solder.

11. The electronic package of claim 1, wherein the thermally conductive filler includes at least one of zinc oxide, aluminum oxide, boron nitride, aluminum

20 nitride, aluminum, copper, silver, indium, and tin.

12. The electronic package of claim 1, wherein the thermally conductive filler comprises between 10% and 90% of the thermal interface material by weight.

13. The electronic package of claim 1, wherein the thermally conductive filler further includes at least one of a surfactant, coupling agent, adhesion modifier, wetting agent, colorant, and stabilizer.

5 14. The electronic package of claim 1, wherein the thermally conductive filler further includes a clay.

15. The electronic package of claim 14, wherein individual platelet particles of the clay have a thickness of less than 2 nm and a diameter greater than 10 nm.

10

16. The electronic package of claim 14, wherein the clay includes at least one of montmorillonite, saponite, hectorite, mica, vermiculite, bentonite, nontronite, beidellite, volkonskoite, magadite, kenyaite, mica, synthetic saponite, synthetic hectorite, fluoronated montmorillonite, and fluoronated mica.

15

17. The electronic package of claim 14, wherein the clay is a swellable free-flowing powder having a cation exchange capacity from about 0.3 to about 3.0 milliequivalents per gram of mineral (meq/g).

20 18. The electronic package of claim 1, wherein the thermal interface material contacts the die on one side and the thermal plate on an opposing side.

19. The electronic package of claim 1, wherein the first device includes a second

thermal plate thermally coupled to the die, the thermal interface material contacting the second thermal plate on one side and the first thermal plate on an opposing side.

5 20. A thermal interface material, comprising:
at least one polyester matrix material; and
at least one thermally conductive filler dispersed in the polyester matrix material.

10 21. The thermal interface material of claim 20, wherein the thermal interface material is a phase change material.

22. The thermal interface material of claim 20, the polyester matrix material is polycaprolactone.

15

23. The thermal interface material of claim 20, wherein the thermally conductive filler comprises between 10% and 90% of the thermal interface material by weight.

24. The thermal interface material of claim 23, wherein the thermally conductive
20 filler further includes a clay.

25. A thermal interface material, comprising:
at least one polyester matrix material have a melting temperature between

40°C and 130°C and improved thermo-oxidative stability compared to a polyolefin resin; and

at least one thermally conductive filler material having a bulk thermal conductivity greater than 50 W/mK and comprising between 10% and 90% of the combination of the polyester matrix material and the thermally conductive filler material by weight.

26. The thermally conductive filler material of claim 25, further comprising a resin additive to modify at least one of modulus, viscosity, and moisture adsorption.

27. The thermally conductive filler material of claim 25, wherein the thermally conductive filler further includes a clay.

1/4




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

INTERNATIONAL SEARCH REPORT

onal Application No

PCT/US2004/024269

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L23/373 H01L23/427

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 067 164 A (SAINT GOBAIN PERFORMANCE PLAST) 10 January 2001 (2001-01-10)	1-3, 6-13, 18-21, 23,25
Y	paragraphs '0028!, '0040! - '0049!, '0058! - '0060!; figures 1,5,6	4,5, 14-17, 22,24, 26,27
X	US 2003/100654 A1 (SCHULTZ WILLIAM J ET AL) 29 May 2003 (2003-05-29)	20-27
Y	paragraphs '0001!, '0029! - '0031!, '0050!; figure 1	4,5, 14-17, 22,24, 26,27
	----- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

° Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

24 November 2004

Date of mailing of the international search report

06/12/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dauw, X

INTERNATIONAL SEARCH REPORT

ational Application No
PCT/US2004/024269

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2002/135984 A1 (WRIGHT DEANNA J ET AL) 26 September 2002 (2002-09-26) paragraphs '0042! - '0045!; figures 4,5 -----	1-3, 9-12, 18-21, 23,25
A	WO 02/081592 A (FURUTANI ORIE ; GELTEC CO LTD (JP); IMAI TAKASHI (JP); MASUDA MASAHICO) 17 October 2002 (2002-10-17) abstract	1-27
P,A	-& EP 1 375 623 A (GELTEC CO LTD) 2 January 2004 (2004-01-02) paragraphs '0001!, '0026! - '0051! -----	1-27
X	US 5 706 579 A (ROSS RICHARD J) 13 January 1998 (1998-01-13) column 3, line 23 - line 46; figures 3,4 -----	1-3, 9-12,14, 18-21, 23-25,27
A	US 5 747 560 A (MAXFIELD MACRAE ET AL) 5 May 1998 (1998-05-05) column 16, lines 41-67 column 6, line 36 - column 7, line 41 -----	1-27

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2004/024269

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1067164	A	10-01-2001	US 6391442 B1	21-05-2002
			CA 2311067 A1	08-01-2001
			DE 60011346 D1	15-07-2004
			EP 1067164 A1	10-01-2001
			JP 2001089756 A	03-04-2001
			US 2003039825 A1	27-02-2003
			US 2004161571 A1	19-08-2004
US 2003100654	A1	29-05-2003	EP 1399519 A1	24-03-2004
			WO 03002682 A1	09-01-2003
US 2002135984	A1	26-09-2002	EP 1354353 A1	22-10-2003
			JP 2004518294 T	17-06-2004
			TW 552690 B	11-09-2003
			WO 02059965 A1	01-08-2002
WO 02081592	A	17-10-2002	JP 2002294269 A	09-10-2002
			CN 1460120 T	03-12-2003
			EP 1375623 A1	02-01-2004
			WO 02081592 A1	17-10-2002
			US 2003180484 A1	25-09-2003
EP 1375623	A	02-01-2004	JP 2002294269 A	09-10-2002
			EP 1375623 A1	02-01-2004
			CN 1460120 T	03-12-2003
			WO 02081592 A1	17-10-2002
			US 2003180484 A1	25-09-2003
US 5706579	A	13-01-1998	US 5572070 A	05-11-1996
			KR 208039 B1	15-07-1999
US 5747560	A	05-05-1998	AT 159270 T	15-11-1997
			CA 2115255 A1	04-03-1993
			DE 69222773 D1	20-11-1997
			DE 69222773 T2	12-02-1998
			EP 0598836 A1	01-06-1994
			JP 2674720 B2	12-11-1997
			JP 6504810 T	02-06-1994
			WO 9304117 A1	04-03-1993
			WO 9304118 A1	04-03-1993